

***Amendments to the Claims:***

This listing of claims will replace all prior versions, and listings, of claims in the application:

***Listing of Claims:***

1. (Currently Amended) A patch comprising a backing layer and an adhesive layer disposed on the backing layer and compounded with an adhesive base agent and pergolide and/or a pharmaceutically acceptable salt thereof, wherein the adhesive base agent comprises an acrylic polymer including no substantial carboxyl group and hydroxyl group in the molecule and having self-adhesion properties, and a rubber polymer, and a basic nitrogen-including polymer including a basic nitrogen and having no self-adhesion property, wherein and a weight ratio of the content of the acrylic polymer to the content of the rubber polymer is from 1:1 to 1:9, and wherein a weight ratio of the total content of the acrylic polymer and the rubber polymer to the content of the basic nitrogen-including polymer is from 9:1 to 1:1.

2. (Cancel)

3. (Currently Amended) The patch according to ~~claim 2~~ claim 1, wherein the basic nitrogen-including polymer is at least one kind selected from methyl methacrylate-butyl methacrylate-dimethylaminoethyl methacrylate terpolymer and polyvinyl acetal diethylamino acetate.

4. (Original) The patch according to claim 1, wherein the adhesive layer further comprises an alicyclic saturated hydrocarbon resin-based tackifier, and a weight ratio of the total content of acrylic polymer and the rubber polymer to the content of the tackifier is from 1:1 to 1:9.

5. (Original) The patch according to claim 1, wherein the acrylic polymer is at least one kind selected from: copolymer of polyacrylate including at least one kind selected from 2-ethylhexyl acrylate, butyl acrylate, diacetone acrylamide and tetraethylene glycol dimethacrylate and polymethyl methacrylate; 2-ethylhexyl acrylate-N-vinyl-2-pyrrolidone-1,6-hexane glycol dimethacrylate terpolymer; and 2-ethylhexyl acrylate-vinyl acetate copolymer.

6. (Original) The patch according to claim 1, wherein the rubber polymer is at least one kind selected from styrene-isoprene-styrene block copolymer, styrene-butadiene-styrene block copolymer, styrene-butadiene rubber, polyisobutylene, isoprene rubber and silicone rubber.

7. (Original) The patch according to claim 1, wherein the rubber polymer is styrene-isoprene-styrene block copolymer.

8. (Original) The patch according to claim 1, wherein the acrylic polymer is at least one kind selected from 2-ethylhexyl acrylate-N-vinyl-2-pyrrolidone-1,6-hexane glycol dimethacrylate terpolymer and 2-ethylhexyl acrylate-vinyl acetate copolymer, and the rubber polymer is styrene-isoprene-styrene block copolymer.

**9.** (Original) The patch according to claim 1, wherein the adhesive layer is compounded with mesylate salt of pergolide.

**10.** (Original) The patch according to claim 1, wherein the adhesive layer further comprises an organic acid.

**11.** (Original) The patch according to claim 10, wherein the organic acid is acetic acid and/or a pharmaceutically acceptable salt thereof.